

6180C3

80 MELT FLOW CLARIFIED RANDOM COPOLYMER FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 6180C3 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding applications that require high melt flow, more stiffness, faster cycle time, low bloom, enhanced processability and excellent clarity. This product contains a new generation clarifier.

Features:

The 6180C3 product provides:

- Low bloom
- High melt flow, excellent processability
- New generation clarifier
- Increased stiffness
- Reduced cycle-time
- Improved color
- Increased stiffness

Typical Properties*

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	80 g/10 min.	80 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Shrinkage	0.015 in/in	0.015 mm/mm	D955
Heat Deflection Temperature at 0.455 MPa (66psi)	172°F	78°C	D955
Tensile yield strength, at 51 mm/min	4100 psi	28.3 MPa	D638 ²
Yield elongation, at 51 mm/min	14%	14%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	160,000 psi	1103 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	0.9 ft-lb/in	48 J/m 4.7 kJ/m ²	D256 ²
% Yellowness Index	Less than -10	Less than -10	
Haze (1.27 mm plaque)	9%	9%	

* Developmental Data taken from a limited database

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of Union Carbide Corporation

Technical data contained herein is furnished without fee or obligation, and is given and accepted at recipient's sole risk. Since conditions of use may vary and are beyond our control. Pinnacle Polymers makes no representation about and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects, industrial hygiene requirements, or other matters associated with particular application of any product described herein. Pinnacle Polymers disclaims any warranty, expressed or implied, regarding the information contained herein, including the implied warranty of merchantability of fitness for a particular purpose.
 .020514