



LONGHORN POLYMERS EVA UE1825

Ethylene Vinyl Acetate

Trade Specs

Property	Value	ASTM
Melt Index (g/10 min)	2.0	D 1238
Vinyl Acetate Content	18%	
Tensile Strength at Yield		
MD	5940	D 882
TD	4390	
Tensile Strength at Break (psi)		
MD	679	D 882
TD	624	
Elongation at Yield (%)		
MD	410	D882
TD	563	
Elongation at Break (%)		
MD	9	D882
TD	9	
Dart Drop Impact Strength, F (g)	606	D 1709
Low Temperature Brittleness (C)	<-76	D 746
Vicat Softening Point (C)	65	D 1525
Hardness, Shore A	91	D 2240

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.