

<u>Resin Properties</u> ⁽¹⁾	<u>Typical Value</u>	<u>ASTM Method</u>
Melt Flow Index, g/10 min		D 1238
190°C/2.16 kg	0.35	
190°C/21.6 kg (HLMI)	30.0	
Density, g/cm ³	0.955	D 792
Melting Point, °F	264	D 3417

Mechanical Properties⁽¹⁾⁽²⁾

Tensile Strength at Yield, psi	4,000	D 638, Type IV specimen, 2 in/min
Elongation at Break, %	600	D-638, Type IV specimen, 2 in/min
Flexural Modulus, psi	200,000	D 790
ESCR ⁽³⁾ , hrs	35	D 1693, B 10% Igepal

Processing

Recommendation

Blow Molding Stock Temperature	360 – 400 °F
Extrusion Melt Temperature	380 – 420 °F

HDPE BLOW MOLDING RESIN⁽⁵⁾

Characteristics

- Good stress cracking resistance
- Excellent stiffness
- ASTM D 1248 – Type III, Class A, Category 5
- Drug Master File listed
- USP Class VI approved
- FDA compliant⁽⁴⁾
- UL 94HB/746 certified

Applications

- Bleach and Detergents
- Industrial chemicals
- Industrial parts
- Suitable for food packaging

5502 12/99

- (1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
(2) The data listed were determined on compression molded specimens and may, therefore, vary from specimens taken from molded articles.
(3) Environmental Stress Crack Resistance (ESCR)
(4) Complies with FDA 21 CFR § 177.1520, Para. (c) 2.1 and 2.2
(5) Anti-stat version available